

Technical Properties

Properties	Standard	Heveatech
Density	ASTM D143-94 2000 (sec 19)	820 kg / m ³
Elasticity (MOE)	JAS 2008 FOR LVL (art 4)	1000.45 kgf / mm ²
Breaking Point (MOR)	JAS 2008 FOR LVL (art 4)	8.16 kgf / mm ²
Compression	ASTM D143-94 2000 (sec 9)	5.30 kg
Janka	ASTM D1037	1800 lbs
Radial & Tangential Shrinkage	ASTM D143-94 2000 (sec 20)	1.5%
Delamination Test	JAS 2008 FOR LVL (art 4)	100% Pass
Scratch Test	JPIC - ew	100% Pass
Nail Holding	JIS Z 2102	185.65 kg
Anti-Termite	JIS K 1571 2004	Yes

